



SLICK'EM

DESCRIPTION: SLICK'EM is trowel-grade micro topping of Portland cement, fine aggregates and proprietary admixes. SLICK'EM may be applied to properly prepared and sound interior substrates creating a new canvas that may be stained, sanded and scored.

SURFACE PREPARATION: We recommend preparation of the substrate be performed in accordance with the ICRI Guideline No. 03732, minimum concrete surface profile (CSP) of 1. This will insure that the surface is clean, dry and free of grease, oil, and sealers and open to receive SLICK'EM.

MIXING: Start by dry mixing contents first. Suggested Ratios: 1.5 to 2 gallon water. Mix well until the SLICK'EM is a thin creamy consistency.

APPLICATION: Before applying SLICK'EM, dampen the substrate with a solution of 1 part SS Polymer to 2 parts water. Pour the SLICK'EM onto the dampened substrate in a long thin line. Spread with a metal squeegee, hand trowel, or magic trowel. Apply as thin as possible while maintaining a wet edge. Allow the first coat to thoroughly dry before applying the second layer. Two applications are recommended. A buffer and a sanding screen will remove trowel marks on the hardened surface.

COLORING: If staining the SLICK'EM surface, it is recommended to create a sample surface on which to test different dilution rates. A rule of thumb may be to start with a 10-part water to 1 part acid stain solution. SLICK'EM may be colored integrally or with the SS Acid Stain and the SS Rainbow System.

LIMITATIONS: SLICK'EM is not a heavy build product and an interior use product only. Do necessary patching and filling prior to applying SLICK'EM.

TECHNICAL DATA:

- Finish.....Must be top coated with a solvent or water base sealer
- Coverage.....1500/2500 sq. ft depending on surface profile
- Drying Time (re-coat).....4 hours at 72°F (Drying time is affected by the thickness of application, humidity, and circulation etc.)
- Drying Time (staining)....Overnight*
- Clean up.....Warm, soapy water

CAUTION: Keep out of reach of children.



Distributed by Cimarron Wholesale | 125 NE 40th Street
Oklahoma City, OK 73105 | Phone 866-906-2006 / Fax 405-526-2008

March 15, 2010