



# SUPREME 2500 GLOSS

**DESCRIPTION:** SS Supreme 2500 Gloss is used as a curing and sealing compound for commercial and industrial applications such as floors, parking decks, broom finished driveways, and sidewalks. SS Supreme 2500 Gloss can be applied stamped, decorative or stained concrete as well as brick, block, stone, patio pavers, broom finished and aggregate driveways. SS Supreme 2500 Gloss is a penetrating, non-yellowing 100% pure acrylic formula.

**BENEFITS:** Used as a curing and sealing compound for commercial and industrial applications such as floors, parking decks, broom finished driveways, and sidewalks. SS Supreme 2500 Gloss can be sprayed, brushed or rolled on stamped, decorative or stained concrete as well as brick, block, stone, patio pavers, broom finished and aggregate driveways.

**SURFACE PREPARATION:** Surface to be coated must be free from all contaminants (dirt, grease, oil, etc). If surface has been stained with an acid based colorant or cleaned with acid or another type of cleaner, be sure to thoroughly rinse substrate prior to applying SS Supreme 2500 Gloss.

**DIRECTIONS:** Apply SS Supreme 2500 Gloss with a roller, HVLP, airless or metal pump-up sprayer. Apply SS Supreme 2500 Gloss in two thin coats, avoid puddling. Cooler morning temperatures are best and with temperatures between 50° and 80° F. Bubbling and blistering tend to form in the afternoon. Conduct tests whenever possible to confirm color choices and application techniques prior to application.

#### **TECHNICAL DATA:**

|                                  |   |
|----------------------------------|---|
| Solids.....                      | 25%   |
| Finish .....                     | High Gloss  |
| Application temperature .....    | Above 40°F below 80°F                               |
| Drying time (to touch) .....     | 30 minutes to an hour at 70°F                       |
| Drying time (light traffic)..... | 12 to 15 hours at 77°F                              |
| Recoat time .....                | 4 to 24 hours                                       |
| Coverage .....                   | 300 to 400 square feet trowled: 200 sq. ft. stamped |
| Clean up .....                   | Xylene  |
| Blush Resistance.....            | Good  |
| Solvent Resistance.....          | Minimal   |
| Concrete Adhesion.....           | Excellent   |

#### **SPECIFICATIONS:**

ASTM C 309 Type 1 CLASS A & B  
ASTM C 1315 Type 1 CLASS A  
Dried Coating is USDA accepted

**WARNING:** • Combustible liquid (Flash Point 105°F). • Keep away from open flames and heat. Do not smoke. • **KEEP OUT OF REACH OF CHILDREN.** • Protect from freezing. • Avoid direct contact with skin. Eye irritation may occur. Wear protective goggles and neoprene gloves. Wash thoroughly after handling. • Use in well-ventilated area. Inhalation of vapors may cause breathing difficulties. HVAC ventilation ducts should be blocked prior to application to avoid solvent fumes being distributed. • VOC Content: meets VOC content limit of <700 grams/liter. • Dispose of this product in accordance with all applicable state and local laws. • Please be aware that this product when cured may be slippery when wet. • Product may darken the surface once coated. Test prior to use. • Apply in two thin coats, not one thick coat. Do not thin material, may cause sealer to delaminate in a short time frame.

**CAUTION:** This product should be used only as directed and in accordance with the control procedures SS has established for a specific application.

March 15, 2010



Distributed by Cimarron Wholesale | 125 NE 40th Street  
Oklahoma City, OK 73105 | Phone 866-906-2006 / Fax 405-526-2008